TECHNICAL SPECIFICATIONS

Work Size		Coverage/Box		Avg. Wt./Box	Avg. Wt./Sq. Mtr. (Kgs.)	
Dimensions (in mm) Thickness (in mm)		(Sq. Mtrs.)	No. of Tiles Per Box	(Kgs.)		
1200x1800mm	9.0	4.32	2	88.00 (Approx)	20.37	

.No.	Characteristics	Group Blb-ISO 13006:2018-09 Nominal Size (N) N ≥ 15cm Whichever is less is applicable		Our Value	Method of Testing
		%	ММ		
1	Deviation in Length & width	± 0.3	± 1.0	± 1.0 mm	ISO - 10545-2
2	Deviation in Thickness	± 5.0	± 0.5	± 0.5 mm	ISO - 10545-2
3	Deviation in Straightness of sides	± 0.3	± 0.8	± 0.8 mm	ISO - 10545-2
4	Deviation in Rectangularity	± 0.3	± 1.5	± 1.5 mm	ISO - 10545-2
5 -	Surface Flatness				ISO - 10545-2
	a. Centre Curvature (max.)	± 0.4	± 1.8	± 1.8 mm	ISO - 10545-2
	b. Edge Curvature (max.)	± 0.4	± 1.8	± 1.8 mm	ISO - 10545-2
	c. Corner Warpage (max.)	± 0.4	± 1.8	± 1.8 mm	ISO - 10545-2
6	Surface Quality	A min. 95% of the tiles are to be free from visible defects		A min. 95% of the tiles are to be free from visible defects	ISO - 10545-2
7	Water Absorption	$0.5\% < \text{Eb} \leq 3\%$ Ind. Max. 3.3%		2.0 - 3.0 %	ISO - 10545-3
8	Abrasion Resistance	Report abrasion class and cycles passed		PEI class 3 min	ISO - 10545-7
9	Modulus of Rupture N/mm2	Min. 30, Individual Min. 27		Min. 30, Individual Min. 27	ISO - 10545-4
10	Breaking Strength (in Newtons)	a. Thickness ≥ 7.5 mm, not less than 1100 b. Thickness < 7.5 mm, not less than 700		Thickness ≥ 7.5 mm, not less than 1100	ISO - 10545-4
11	Crazing Resistance	Required		4 cycle at 7.5 bar min.	ISO - 10545-11
2	Resistance to staining	Min. Class 3		Min. Class 3	ISO - 10545-14
13	Resistance to Chemical	Test method available		Resistance to specified chemicals	ISO - 10545-13
4	Moisture Expansion in millimetres per metre	Test method available		Negligible	ISO - 10545-10
15	Thermal Shock Resistance	Test method available		No damage	ISO - 10545-9

<sup>Colours in the catalogue are as accurate as printing process allows. please check actual tile sample before making the final selections.
Sizes mentioned in the catalogue are nominal sizes only.
No claim will be entertained once the tiles are fixed.
For better laying, please follow the instructions on the packaging box.
Please make sure to check the shade/finish with the sales agent/ dealer before making the final purchase because there might be variation in actual finish that shown in the catalogue. The company will not bear any loss in such case.</sup>