Pavigres

Heavy Duty Full Body Paving Tiles

Work Size		Pieces/Box	Coverage/Box	Weight/Box	Weight/Sq.Mtr	
Dimensions (in mm)	Thickness (in mm)	(nos.)	(sq.mtr.)	(kgs.) (Approx)	(kgs.) (Approx)	
300x300 (Rectified)	9.50	8	0.72	14.50	20.14	

Comparison of Kajaria Tiles Parameters to International Standards IS:4457:2007								
	S.No.	Characteristics	I.S4457 : 2007	Our Value	Method of test, Ref to Annex			
1 = 2 = 3 = 4 = 4 = 4	1	Deviation in Length & Width (from work size)	±0.6%	±0.1%	Annex - B			
7	2	Deviation in Thickness	±5%	±5%	Annex - B			
	3	Straightness of Sides (Facial)	±0.2%	±0.2%	Annex - B			
	4	Rectangularity	±0.2%	±0.2%	Annex - B			
_	5	Surface Flatness (%)	±0.3%	±0.3%	Annex - B			
	6	Surface Quality	Min. 95% free from visible defects	Min. 95% free from visible defects	Annex - B			
A ST	7	Water Absorption by weight	Average < 0.5% Individual 0.6 max	Average $< 0.5\%$ individual 0.6 Max.	Annex - C			
5	8	Breaking Strength (N)	1300 Min.	1300 Min.	Annex -D			
<u></u>	9	Modulus of Rupture (N/mm2)	Average - 35, Individual, min 32	Average - 35, Individual, min 32	Annex - D			
<u>©</u>	10	Deep Abrasion Resistance (mm3)	175 Max.	175 Max.	Annex - E			
_	11	Chemical Resistance Resistance to chemicals	Required as agreed between Manufacturer and Purchaser	Required as agreed between Manufacturer and Purchaser	Annex - F			
		Resistance to concentrated HN03 and H2SO4	Loss in Mass - 1.5% max.	Loss in Mass - 1.5% max.	Annex - G			

- Colours in the catalogue are as accurate as printing process allows. please check actual tile sample before making the final selections.
 Sizes mentioned in the catalogue are nominal sizes only.
 No claim will be entertained once the tiles are fixed.
 For better laying, please follow the instructions on the packaging box.
 Please make sure to check the shade/finish with the sales agent/ dealer before making the final purchase because there might be variation in actual finish that shown in the catalogue. The company will not bear any loss in such case.

